



AESSEAL PACKING STYLE 270

Combination Braid of ePTFE with Incorporated Graphite and Para-Aramid Fiber Surface reinforcement with Silicone Run In Lubricant

Characteristics

- · Even and reduced shaft surface wear
- · Excellent heat conductivity
- Recommended shaft surface hardness: HRC 45
- · Safe and universal packing with abrasive media

Operating range

| | \bigcirc | 1 | I |
|-------------------|------------|--------|-----|
| p [bar] | 25 | 250 | 150 |
| v [m/s] | 20 | 2 | |
| t°C | -100 | . +280 | |
| рН | 2 - 12 | 2 | |
| g/cm ³ | 1.50 | | |

Main application

- Centrifugal pumps
- Mixer
- Kneader
- · Agitators
- Filter
- Refiner

Suitable for

- Chemical industry
- · Pulp and paper industry
- · Waste water technology

Variant

Style 274 with Para-Aramid Cornerreinforcement, available 6 mm and above

Practical useful application data: max. temperature: +200 °C max. pressure centrifugal pumps: 20 bar

Reinforcedcornersfor

oscillating plungers

Reinforcedrunningtrack

forrotatingshaftsagainst churningproductparticles

Form of delivery

This packing can be manufactured from 4 to 40 mm square as well as in intermediate, inch sizes and special measurements.

04 - 09 mm on 1 kg spool 10 - 15 mm on 2,5 kg spool 16 - 25 mm on 5 kg spool

Special length, pre-cut or die formed rings on request.

1 kg of packing of the following cross-sections is equivalent to displayed meter lengths:

| Size mm | Meter | Size mm | Neter |
|------------|-------|------------|-------|
| 4 | 41.7 | 13 [1/2"] | 4.1 |
| 5 [3/16"] | 26.7 | 14 [9/16"] | 3.4 |
| 6 | 18.5 | 15 | 3.0 |
| 6.4 [1/4"] | 16.5 | 16 [5/8"] | 2.6 |
| 8 [5/16"] | 10.4 | 18 | 2.1 |
| 9.5 [3/8"] | 7.4 | 19 [3/4"] | 1.8 |
| 10 | 6.7 | 20 | 1.7 |
| 11 [7/16"] | 5.4 | 22 [7/8"] | 1.4 |
| 12 | 4.6 | 25 [1"] | 1.1 |

All technical information and advice is based on our experience and will be given most conscientiously but without any liability.

Indication and figures are for guidance only and need to be examined by the user. All sizes are subject to manufacturing tolerances. We reserve the right to modify specifications at any time. Please note that the technical values cannot be used all at the same time in their maximum values.

AESSEAL plc Packing Division Europe Rudolf-Diesel-Ring 26a . 82054 Sauerlach . Germany

Telephone: +49 8104 6640-21 . Telefax: +49 8104 6640-44 packing.euro@aesseal.com . www.aesseal.com

www.aesseal.com